

NOURYBOND[®] 272

Adhesion Promoter

DESCRIPTION

Nourybond 272 adhesion promoter is a modified polyamidoamine PVC plastisol adhesion promoter intended for use in automotive sealants and underbody coatings. It is designed to provide adhesion to electrodeposition primers used in the manufacture of automobiles, trucks, and buses.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear amber liquid		
Colour	max. 10	Gardner	ASTM D 1544-80
Viscosity @ 25°C	15-35	Pa.s	Brookfield RVTD, Spindle 4
Amine Value	185-200	mg KOH/g	Perchloric Acid Titration
Recommended Use Level	1-4	wt %	In PVC plastisol formulation

ADVANTAGES

- 130°C cure
- High amine value
- Provides adhesion to a wide variety of automotive electrodeposition primers

APPLICATIONS

- Underbody coatings
- Non-visible seam sealers

SHELF LIFE

At least 12 months from the date of manufacture in the original sealed container at ambient temperature.

STORAGE AND HANDLING

Due to the nature of Nourybond 272, phase separation may occur during storage. Moisture and elevated temperatures can promote this effect, which is irreversible and may affect the performance of the product. It is therefore strongly recommended to store the product between 5 and 23°C and away from moisture. In general, it is recommended to mix the product thoroughly before use.

Also refer to the Safety Data Sheet for Nourybond 272 adhesion promoter.

TYPICAL CURE SCHEDULE

30 min @ 130°C

Nourybond® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

