

ANCAMIDE® 221-X70

Curing Agent

DESCRIPTION

Ancamide 221-X70 curing agent is a member of a new series of reactive polyamides developed for use in the curing of epoxy resins in solvent-based surface coatings applications. Ancamide 221-X70 is TETA free and supplied at 70% solids in xylene. Special features include good colour, colour stability, chemical resistance and excellent corrosion resistance properties. It is freely compatible with a wide range of solvents, including those generally used in epoxy resin based coatings.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear Amber Liquid		
Colour	9 max	Gardner	ASTM D 1544-80
Viscosity @ 25°C	1,000-2,500	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	155±10	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	0.94		
Equivalent	340	Wt/{H}	
Recommended Use Level	50-70		With Bisphenol A diglycidyl ether (EEW=500)
Solids Content	70±2	%	

ADVANTAGES

- Good corrosion resistance
- Rapid touch dry with solid epoxy resins
- Good colour and light stability
- Compatible with wide range of solvents

APPLICATIONS

- Solvent based marine and protective coatings
- Primers, sealers and coatings for concrete

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 221-X70 curing Agent.

TYPICAL HANDLING PROPERTIES' [@ 50 PHR]

Property	Value	Unit	Method
Pot Life	>7h	h	Clear coat formulation, time to double in viscosity
Thin Film Set Time	4.5	h	BK Drying Recorder Phase II
Set to touch (finger)	1.5	h	
Hard dry thumb twist	7.5	h	

TYPICAL CURE SCHEDULE

(i) 2-7 Days at Room Temperature

FILM PROPERTIES AFTER 10 DAYS CURE @ 23°C¹

Property	Value	Unit	Method
Perzoz Hardness	315		
Direct impact	200	cm.kg	
Reverse impact	200	cm.kg	
Flexibility Cylindrical Mandrel	3	mm pass	Erichsen mandrel tester 266

(1) With Bisphenol A diglycidyl ether (EEW=500)

SUPPLEMENTARY DATA

Ancamide 221-X70 curing agent is low viscosity, solvent based polyamide, supplied at 70% solids in xylene. The product is intended for use with solvent based solid epoxy resins in the development of high performance, corrosion resistant coatings for the protection of steel and concrete. When used with type 1 solid epoxy resins (DER 671X75 or Epon 1001 X75), Ancamide 221-X70 offers fast lacquer dry, rapid mechanical property development, good adhesion to the steel substrate and excellent long-term humidity and corrosion resistance.

Solvent based coatings can be formulated using this product which can then be used for a wide variety of industrial maintenance and marine applications.

Ancamide 221-X70 has a non-critical loading and can be used at levels ranging from 40 to 100 phr with the preferred range being 50-70 phr (a) with a solid epoxy resin EEW 500.

(a) Equates to a loading of 37.5 - 52.5 parts of Ancamide 221-X70 with 100 parts DER 671-X75 as supplied.

FILM PROPERTIES

In a clear coat formulation Ancamide 221-X70 also exhibits a high degree of flexibility. As shown in Table 1, the direct impact resistance of Ancamide 221-X70 is comparable to Ancamide 220-X70 and superior to Ancamide 350A. Ancamide 221-X70 also shows excellent reverse impact resistance (200 cm.kg). Ancamide 221-X70 formulations can also be accelerated using Ancamine® K54 (phenolic, tertiary amine accelerator). Levels can be varied to achieve the desired dry speed properties, with the preferred level in the 2.5-5.0% range based on Ancamide 221-X70 use level.

TABLE 1: CLEAR COAT PERFORMANCE PROPERTIES

Property	Ancamide 221-X70	Ancamide 220-X70	Ancamide 350A ^(*)
Direct Impact	200	200	40
Reverse Impact	200	200	10
Dry Speed BK Phase II [h]	4:30	6:00	10:00
Dry Speed (+2.5% K54)	2:00	2:30	5:30
Specular Gloss 60#	142	140	95
Pendulum Hardness	80	70	45
Day 1	205	200	89
Day 3	300	300	120
Day 14			
Conical Mandrel Bend	Pass	Pass	Pass
Cylindrical Mandrel Bend (mm pass)	3	3	ND
Cross Hatch Adhesion (dry)	Gt0	Gt0	Gt0

*Ancamide 350A tested with liquid Bis A diglycidyl ether (EEW 190); Cross hatch adhesion Gt0 = no loss of adhesion

STARTING POINT FORMULATIONS

Appendix 1 contains preliminary start point formulations based on Ancamide 221-X70 curing agent for a clear coat and an anti-corrosive primer. When pigmented, Ancamide 221-X70 coatings exhibit a fast lacquer dry, as measured using the “finger” dry to touch method, where coatings are dry to touch in less than 2 hrs. Using the “Beck Koller” method, dry-hard times range from 5-9 h depending upon the system tested, when applied and cured at 23°C. As with all solvent based coatings, dry times are influenced by solvent choice, so dry times may vary depending upon the ratio of polar and non-polar solvents incorporated into the coating formulation. Pot lives as measured by the time for the mix to double in viscosity are in the 6-8 hours range, which is typical for such solvent based polyamide systems.

Formulation A221X70P1 (page 6) is a low volume solids (43%), medium PVC (34%) primer, with a 3:1 mix ratio by volume, based on epoxy resin to amine hardener. The initial viscosity of the formulated resin base is 2,300mPa.s and the mix viscosity of the system is 500mPa.s with a total VOC of 485g/l. The primer formulation is compatible with a variety of different let down solvents (including xylene, n-butanol, MIBK, methoxy-propanol, etc) and can be further let down if required for additional spray applications. The coating formulation can be applied with conventional spray equipment or brush applied to the steel substrate. After application the primer is dry to handle after 5 h.

Formulation A221X70P1 has been evaluated for corrosion resistance properties using salt spray, humidity and prohesion resistance accelerated weather tests. After 1000 hrs exposure, coatings exhibit excellent corrosion resistance. No signs of field blisters have been detected using the above weather tests, with panels exhibiting no scribe creep in the salt spray test and some minor damage around the scribe when subjected to the prohesion test study. For comparative purposes, Ancamide 220-X70 was also included in the test study as the “industry” standard reference. In all the corrosion resistance tests carried out, both Ancamide 221-X70 and Ancamide 220-X70 demonstrated comparable performance.

PERFORMANCE EVALUATION

All coatings were evaluated in 5% salt spray, and in continuous humidity at 35°C. They were also evaluated using a prohesion - cyclic weathering tester, and Cleveland — constant humidity exposure, following a 10 day ambient cure of applied Coatings.

Coatings were applied to grit blasted, hot rolled steel (SA2.5), using conventional spray equipment, in double coats to give coatings with a 75-100µ dry thin thickness (DFT). In salt spray, (ASTM B-117) panels were scribed and evaluated for field blisters using the US Federal Standard Test Method 141a, Method 6461 and the scribe creep was rated in accordance with ASTM D-1654. Similar evaluations were made for panels placed in the prohesion cabinet (ASTM G85-94). Panels exposed to humidity were not scribed and coatings were assessed for blistering only. These tests also included evaluations for changes in visual appearance.

CORROSION RESISTANCE: Anti-corrosion resistant primers based on Ancamide 221-X70 and Ancamide 220-X70, were evaluated for salt spray and constant humidity resistance. The results obtained are presented in Table 2-4. Following 1000h salt fog exposure, formulations A221-X70P1 and A220-X70P1 both exhibit excellent resistance. Both formulations also demonstrated excellent humidity resistance with no signs of field blistering being observed following 2000 hrs continuous testing.

TABLE 2: SALT SPRAY RESISTANCE - ANCAMIDE 221-X70 AND ANCAMIDE 220-X70 [1000H]

Formulation	Scribe Creep	Field Blistering	Blister Size
A221-X70P1	10	10	10
A220-X70P1	9	10	10
5% salt spray, cabinet temperature 35oC — ASTM B-117, film thickness 75-100μ. Rating: 10 = Best (no blisters), 0 = Worst			

TABLE 3: PROHESION EXPOSURE - ANCAMIDE 221-X70 AND ANCAMIDE 220-X70 [1000H]

Formulation	Scribe Creep	Field Blistering	Blister Size
A221-X70P1	7	10	10
A220-X70P1	6	10	10
Prohesion ASTM G85-94 Film thickness 75-100μ. Rating: 10 = Best, 0 = Worst For blister size, rating 10 = no blisters observed			

TABLE 4: CLEVELAND HUMIDITY EXPOSURE - ANCAMIDE 221-X70 AND ANCAMIDE 220-X70 [2000H]

Formulation	Field Blistering	Blister Size
A221-X70P1	10	10
A220-X70P1	10	10
Continuous 100% humidity exposure — ASTM D-2247, cabinet temperature 50#C Film thickness 75-100μ. Rating: 10 = Best, 0 = Worst For blister size, rating 10 = no blisters observed		



APPENDIX I

ANCAMIDE 221-X70 CLEAR COAT FORMULATION

			Clear Coat
A-Component (g)			
1. Epoxy Resin	DER 671X75	Olin	410.00
2. Solvent	MIBK		80.00
3. Solvent	Dowanol PM		10.00
			500.00
A-Component Manufacture Procedure:			
Charge components 1-3 and stir homogeneous at low shear			
B-Component (g)			
1. Curing Agent	Ancamide 221-X70	Evonik	155.00
2. Solvent	Xylene		140.00
3. Solvent	Dowanol PM		140.00
			435.00
Total			935.00
After mixing Part A and B, apply a 15-30 minute induction time prior to application.			



TECHNICAL DATA

Mixing Ratio	Weight	1.1 :1
	Volume	1.0: 1
Density (g/ml)	- Part A	1.02
	- Part B.	0.93
	- Mix	0.98
Solid Content (weight %)	- Part A	61.5
	- Part B.	25.0
	- Mix	44.5
VOC	g/l	540
Mix Viscosity @ 25°C	mPa.s	300
Pot-life	h	7
Gloss (60°)		142
BK Dry time 23°C	h	1.30
Phase I	h	4.30
Phase II	h	9.30
Phase III		
Hard Dry Thumb Twist	h	3:1
Persoz Hardness	14 days	300
MEK Double Rubs		>200

ANCAMIDE 221-X70P1 ANTI-CORROSIVE PRIMER FORMULATION

Anti-Corrosive Primer

A-Component (g)

1. Epoxy Resin	DER 671X75	Olin	280.00
2. Solvent	MIBK		80.00
3. Solvent	Xylene		110.00
4. Epoxy Resin	n butanol		40.00
5. Epoxy Resin	Blanc fix micro		100.00
6. Epoxy Resin	Talc 10MO		100.00
7. Epoxy Resin	Heucophos ZPO	Heubach	140.00
8. Epoxy Resin	Bayferrox 130M	Bayer	150.00
			1,000.00

A-Component Manufacture Procedure:

- Charge components 1-3 and stir homogeneous at low shear
- Slowly add components 5-8 and then mix under high shear for 15-30 mins until Hegman gauge 7 is achieved

B-Component (g)

1. Curing Agent	Ancamide 221-X70	Evonik	106.00
2. Solvent	Xylene		59.00
3. Solvent	Dowanol PM		35.00
			200.00
Total			1,200.00

After mixing Part A and B, apply a 15-30 minute induction time prior to application.

TECHNICAL DATA

Mixing Ratio	Weight	5.0 :1
	Volume	3.0 :1
Density (g/ml)	- Part A	1.51
	- Part B.	0.92
	- Mix	1.37
Solid Content (weight %)	- Part A	70.0
	- Part B.	37.1
	- Mix	64.5
Solid Content (Volume %)	- Part A	46.0
	- Part B.	31.5
	- Mix	42.5
Mix Viscosity @ 25°C	mPa.s	300
VOC	g/l	484
PVC	%	33.8
Pot-life	h	7
Gloss (60°)		25
BK Dry time 23°C	h	1.30
Phase I	h	4.00
Phase II		
Hard Dry Thumb Twist	h	3.00
Persoz Hardness	7 days	185
Direct impact	cm.kg	200
Reverse impact	cm.kg	180

1. An additional 20g of xylene/n-butanol (1:1) solvent added to achieve desired spray viscosity

* Reference formulation A220-X70P1 is as above but substituting the Ancamide 221-X70 curing agent with Ancamide 220-X70

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProdinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

