

**ANCAMIDE<sup>®</sup> 2781****Curing Agent****DESCRIPTION**

Ancamide 2781 curing agent is a versatile, low viscosity hardener designed to cure liquid epoxy resins at elevated temperatures. The unique chemistry offers a longer working time than traditional amidoamines. This can enhance the processing of complex weaved fabric by optimum fiber wetting, minimized material waste and improved overall throughput and provide an overall excellent balance of pot life and low temperature cure. It is recommended for use in cure-in-place-pipe, composite processing, electronics and industrial electrical applications.

**TYPICAL PROPERTIES**

Property	Value
Appearance	Amber Liquid
Color (Gardner)	max. 12
Viscosity <sup>1</sup> @ 25 °C (mPa.s)	80-120
Specific Gravity @ 25°C (g/cm <sup>3</sup> )	0,92
Equivalent Wt/[H]	104
Recommended Use Level <sup>2</sup> (PHR)	55

**TYPICAL HANDLING PROPERTIES<sup>2</sup>**

Property	Value
Mixed Viscosity <sup>1</sup> @ 25 °C (mPa.s)	850
Gel Time <sup>3</sup> 150g mix @ 25 °C (min)	400-500
Time to 10,000 mPa.s. <sup>1</sup> @ 25 °C (min)	425

**ADVANTAGES**

- Longer working time
- Low exotherm
- Low viscosity

## APPLICATIONS

- Cure-in-Place-Pipe
- Composites – Filament winding, VARTM
- Resin Infusion
- Potting and encapsulation

## TYPICAL CURE SCHEDULE

- 2 h @ 65°C
- Post cure at higher temperatures (100°C) can be accomplished depending on processing flexibility and final product performance needs.

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 2781 curing agent.

## THERMAL PERFORMANCE<sup>2</sup>

**Glass Transition Temperature<sup>4</sup> 61°C**  
**Glass Transition Temperature<sup>5</sup> 53 °C**

## MECHANICAL PERFORMANCE - CAST PANEL<sup>2</sup>

Property	Value
Flexural Strength	51 MPa
Flexural Modulus	2.3 GPa
Tensile Strength	51 MPa
Tensile Modulus	1.8 GPa
Tensile Elongation @ Break	6%
Compressive Strength	42 MPa
Compressive Modulus	0.968 GPa

## MECHANICAL PERFORMANCE - COMPOSITE PANEL<sup>2</sup>

Property	Value
ILSS 0° Longitude / 90° Transverse (ASTM D2344)	38/15 MPa
Flexural Strength - Composite 0° Longitude (ASTM D790)	897 MPa
Flexural Modulus - Composite 0° Longitude	42.1 GPa

- (1) Brookfield RVTD, spindle 27
- (2) Bisphenol-A based epoxy resin (EEW=190)  
Cure schedule cast and composite panel: 2 h @ 150°F/65°C  
Composite panel by vacuum-assisted resin transfer molding  
Fiber type: E-glass (275 g/m<sup>2</sup>) Unidirectional  
Fiber volume: 60 ± 3 %
- (3) Techne Gelation Timer, 150 g mix
- (4) DSC @ 10°C/min second heating scan
- (5) DMA @ 3°C/min- Three point bending (Tan Delta)

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

### EVONIK OPERATIONS GMBH

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

### EVONIK CORPORATION

Business Line Crosslinkers  
7201 Hamilton Blvd.  
Allentown, PA 18195  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

### EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

