

ANCAMIDE[®] 3009**Curing Agent****DESCRIPTION**

Ancamide 3009 curing agent is a polyamide in xylene/methoxypropanol (4:1). The curing agent is supplied at 60% solids and is recommended for use with solid epoxy resin solutions to provide coating systems offering good corrosion resistance.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear amber liquid		
Colour	≤ 10	Gardner	ASTM D 1544-80
Viscosity @ 25°C	2200-3500	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	50-56	mg KOH/g	Perchloric Acid Titration
Solids Content	60+/-2	%	
Specific Gravity @ 21°C	0.94		
Equivalent	800	Wt{H}	
Recommended use Level	120	PHR	With solvent based Bisphenol A diglycidyl ether solution (EEW=670)

ADVANTAGES

- Excellent corrosion resistance
- Good adhesion to metal substrates

APPLICATIONS

- Solvent-based coatings
- Marine and Protective Coatings

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 3009 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit	Method
Gel Time (250g mix at 23°C)	500-1000	mins	Techne GT-3 Gelation Timer
Typical cure schedule	2-7	days	

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

