

Product information

ANCAMIDE[®] 3112

Curing Agent

DESCRIPTION

Ancamide 3112 curing agent is a modified polyamide adduct supplied at 62% solids in xylene and n-butanol. The curing agent is recommended for use with solid epoxy resin solutions for the formation of high performance corrosion resistant coatings.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear amber liquid		
Colour	≤ 10	Gardner	ASTM D 1544-80
Viscosity @ 25°C	700-1350	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	143-162	mg KOH/g	Perchloric Acid Titration
Solids	62+/-2	%	
Specific Gravity @ 21°C	0.95		
Equivalent	325	Wt{H}	
Recommended use Level	80	PHR	With solvent based Bisphenol A diglycidyl ether solution (EEW=670)

ADVANTAGES

- Corrosion resistance
- Moderate to fast dry speed

APPLICATIONS

- Solvent based coatings
- Marine and Protective Coatings

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 3112 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit
Typical cure schedule	2-7	days

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

