

## Product information

# ANCAMIDE<sup>®</sup> 3537

## Curing Agent

### DESCRIPTION

Ancamide 3537 curing agent is an accelerated polyamide adduct supplied in a 4:1 xylene/butanol blend. Ancamide 3537 curing agent is recommended for use in marine and industrial maintenance coatings. Ancamide 3537 exhibits long pot life and fast lacquer dry when used with solid epoxy resins.

### TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear amber liquid		
Colour	≤ 10	Gardner	ASTM D 1544-80
Viscosity @ 25°C	400-1,200	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	157-177	mg KOH/g	Perchloric Acid Titration
Solids Content	60+/-2	%	
Specific Gravity @ 21°C	0.95	g/ml	
Equivalent	540	Wt/{H}	
Recommended use Level	80	PHR	With solvent based Bisphenol A diglycidyl ether solution(EEW=670)

### ADVANTAGES

- Long pot life
- Fast lacquer dry

### APPLICATIONS

- Marine and Industrial Maintenance coatings

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 3537 curing agent.

## TYPICAL CURE SCHEDULE

**2-7 days**

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

### EVONIK OPERATIONS GMBH

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

### EVONIK CORPORATION

Business Line Crosslinkers  
7201 Hamilton Blvd.  
Allentown, PA 18195  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

### EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

