

Product information

ANCAMIDE[®] 220

Curing Agent

DESCRIPTION

Ancamide 220 curing agent is one in a series of standard reactive polyamides for use in the curing of epoxy resins. It has been designed particularly for use in solvent-based surface coatings.

Evonik also offers Ancamide 221 curing agent which is similar to Ancamide 220 in performance. Ancamide 221 may be a more cost effective alternative for your formulation.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear, amber liquid		
Color	7	Gardner	ASTM D1544-80
Viscosity @ 77°F	330,000	cP	Brookfield viscosity, ASTM D445-83
Specific Gravity @ 77°F	0.97		
Amine Value	245	mg KOH/g	
Flash Point (closed cup)	388	°F	
Equivalent Wt/{H}	185		
Recommended Use Level with liquid resin	90-100	phr	EEW=190
Recommended Use Level with solid resin	35-10	phr	EEW=510

ADVANTAGES

- Good color and light stability
- Good chemical resistance
- Compatible with a wide range of solvents, including those generally used in epoxy resinbased coatings
- Complies with FDA 21 CFR 175.300, and 175.105

APPLICATIONS

- Solvent-based maintenance coatings
- Primers, sealers and coatings for concrete

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 220 curing agent.

TYPICAL CURE SCHEDULE

2 to 7 days at ambient temperature. Films can be force-dried or baked to accelerate cure. Cure can also be accelerated by the addition of 2–3 phr of Ancamine® K54 curing agent.

CHEMICAL RESISTANCE

Chemical resistance, particularly against water and aqueous media, is strongly influenced by loading of Ancamide 220 curing agent and the choice of solvents. With correct loading and suitable solvent blends, resistance is good to excellent against water and alkali solutions, alcohols, hydrocarbons and certain chlorinated hydrocarbons; acid resistance is moderate to poor.

TYPICAL HANDLING PROPERTIES

Merkmal	Value	Unit
Gel Time (150g mix @ 77°F - with liquid resin, EEW=190)	260	min

TYPICAL PERFORMANCE*

(Cured 7 days @ ambient temp.)	Value	Unit
Bond Strength (mild steel to mild steel)	1,960	psi

*Ancamide 220 curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

