

Product information

ANCAMIDE[®] 2444

Curing Agent

DESCRIPTION

Ancamide 2444 curing agent is a modified polyamide intended for use with epoxy resin in two-component ambient cure systems.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear, Amber liquid		
Color	9	Gardner	ASTM D 1544
Viscosity @ 77°F	6,600	cP	ASTM D 445-83, Brookfield, RVTD, Spindle 4
Specific Gravity @ 77°F	1.02		ASTM D 1475-85
Weight per Gallon	8.53		
Amine Value	300	mg KOH/g	
Flash Point	>200	°F	Seta Flash Closed Cup
Equivalent Wt{H}	125		
Recommended Use Level	60-70	phr	EEW=190

ADVANTAGES

- High resistance to amine blush
- High chemical resistance
- Excellent adhesion
- Good flexibility
- Good cure response

APPLICATIONS

High-solids, corrosion-resistant coatings for marine, industrial maintenance, military and aerospace applications.

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 2444 curing agent.

TYPICAL CURE SCHEDULE

7 days at ambient temperature.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit	Method
Gel Time (150g mix @ 77°F)	95	min	ASTM D 2471-71
Set to Touch	3 hr, 15 min		
Tack Free	5 hr, 30 min		
Dry Hard	7 hr, 30 min		

* Ancamide 2444 curing agent formulated at 60 phr with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

