

Product information

ANCAMIDE[®] 350A

Curing Agent

DESCRIPTION

Ancamide[®] 350A curing agent is one in a series of standard reactive liquid polyamides for use in the curing of epoxy resins.

Evonik also offers Ancamide[®] 351A curing agent which is similar to Ancamide 350A in performance. Ancamide 351A may be a more cost effective alternative for your formulation.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Amber liquid		
Color	7	Gardner	ASTM D1544-80
Viscosity @ 77°F	11,000	cP	Brookfield, ASTM D445-83
Specific Gravity @ 77°F	.97		
Weight per Gallon @ 77 °F	8.1		
Amine Value	380	mg KOH/g	
Flash Point	340	°F	Seat Flash Closed Cup
Equivalent Wt{H}	100		
Recommended Use Level	55	phr	EEW=190

ADVANTAGES

- Low viscosity
- Higher imidazoline content
- Long pot life with liquid resins
- Complies with FDA regulation 21 CFR 175.300; 21 CFR 176.170 and 21 CFR 175.105

APPLICATIONS

- High-solids coatings
- Adhesives and sealants
- Encapsulation
- Castings

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 350A curing agent.

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

TYPICAL CURE SCHEDULE

2 to 7 days at ambient temperature. Films can be force dried or baked to accelerate cure.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit
Gel Time (150g mix @ 77 °F)	200	min
Thin Film Set Time @ 77 °F	11	h

TYPICAL PERFORMANCE*

Property	Value	Unit	Method
Heat Deflection Temperature	124	°F	ASTM D648 at 264 psi
Flexural Strength	10,600	psi	

* Ancamine 350A curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

Ancamide[®] is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

