

ANCAMINE® 1693HV

Curing Agent

DESCRIPTION

Ancamine 1693HV is a modified cycloaliphatic polyamine adduct designed for use as an ambient temperature curing agent for epoxy resin. Ancamine 1693HV light colour, good colour stability and outstanding chemical resistance, particularly to sour crude oil. These properties make Ancamine 1693HV ideal for use in high solids and solvent free storage coatings.

TYPICAL PROPERTIES

| Property | Value | Unit | Method |
|-------------------------|---------------------------|----------|---|
| Appearance | Clear light yellow liquid | | |
| Colour | max 10 | Gardner | ASTM D 1544-80 |
| Viscosity @ 25°C | 2,700-9,200 | mPa.s | Brookfield RVTD, Spindle 4 |
| Amine Value | 300-320 | mg KOH/g | Perchloric Acid Titration |
| Specific Gravity @ 25°C | 1.05 | g/ml | |
| Equivalent | 106 | Wt/{H} | |
| Recommended use Level | 55 | PHR | With Bisphenol A diglycidyl ether (EEW=190) |

ADVANTAGES

- High chemical resistance

APPLICATIONS

- High solids and solvent free coatings
- Chemical storage tanks

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container stored undercover at ambient temperature away from excessive heat and humidity.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 1693HV curing agent.

TYPICAL HANDLING PROPERTIES

| Property | Value | Unit | Method |
|-----------------------------|-------|------|----------------------------|
| Gel Time (150g mix at 25°C) | 60 | mins | Techne GT-3 Gelation Timer |

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

