

**ANCAMINE<sup>®</sup> 2264 AND 2167****Curing Agent****DESCRIPTION**

Ancamine<sup>®</sup> 2264 and Ancamine 2167 curing agents are cycloaliphatic amines designed for use with liquid epoxy resins in the fabrication of industrial composites. Ancamine 2264 and Ancamine 2167 curing agents contain polycycloaliphatic polyamines (high functionality cycloaliphatic amines). Incorporation of polycycloaliphatic polyamines in these curing agents improves stiffness and elevated temperature performance in cured systems as compared with cycloaliphatic diamine cured systems.

**TYPICAL PROPERTIES**

Property	Ancamine 2264	Ancamine 2167	Unit	Method
Appearance	Amber Liquid	Yellow Liquid		
Colour	9	3	(Gardner)	ASTM D 1544-80
Viscosity @ 25°C	2,600	210	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	502	520	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	1.00	0.975	g/ml	
Equivalent	54	53	Wt/{H}	
Recommended use Level	29	28	PHR	With Bisphenol A diglycidyl ether (EEW=182)

**ADVANTAGES**

- Low temperature reactivity
- Rapid development of cure
- Excellent thermal and mechanical performance
- Superior solvent and acid resistance

**APPLICATIONS**

- Filament winding
- Resin transfer molding
- Compression molding
- Tooling
- Safer alternative to Aromatic Amines

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature.

## STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2264 and Ancamine 2167 curing agent.

## TYPICAL HANDLING PROPERTIES<sup>1</sup>

Property	Ancamine 2264	Ancamine 2167	Unit	Method
Mixed Viscosity @ 25°C	5,800	2,340	mPa.s	Brookfield RVTD, Spindle 4
Gel Time (150g mix @ 25°C )	195	210	mins	Techne GT-3 Gelation Timer
Stroke Gel Time (150°C)	105	100	sec	
Stroke Gel Time (175°C)	50	42	sec	

## TYPICAL PERFORMANCE PROPERTIES<sup>1,2</sup>

Property	Ancamine 2264	Ancamine 2167	Unit	Method
Glass Transition Temperature	162	161	°C	DSC Method
Tensile Strength	72	76	MPa	ISO 527
Tensile Modulus	2,670	2,560	MPa	ISO 527
Flexural Strength	134	131	MPa	ISO 178
Flexural Modulus	3,450	3,050	MPa	ISO 178
Plain Strain Fracture Toughness	0.75	0.78	MPa√m	
Stain Energy Release rate	177	205	Pa.m	

<sup>1</sup> With Bisphenol A diglycidyl ether (EEW=182)

<sup>2</sup> Cure Schedule: 30 min at 80°C plus 3 hrs at 150°C

## SUPPLEMENTARY DATA

### LOW-TEMPERATURE REACTIVITY AND RAPID DEVELOPMENT OF CURE

Ancamine 2264 and Ancamine 2167 curing agents react readily with epoxy resin at temperatures less than 100°C. This low-temperature reactivity contributes to rapid viscosity build before and during the initial stages of cure. Although rapid viscosity build before cure can shorten pot life, it can also reduce resin loss during composite part fabrication. Ancamine 2264 and Ancamine 2167-based formulations, with a low viscosity diglycidyl ether of bisphenol-F (DGEBF) epoxy resin, offer a 30 to 40% viscosity reduction compared with standard diglycidyl ether of bisphenol-A (DGEBA) epoxy resin formulations. Such formulations also maintain a 2-to-3 hour pot life.

FIGURE 1: RESIN BATH BEHAVIORS FOR ANCAMINE 2264 AND ANCAMINE 2167 WITH DGEBA EPOXY RESIN




FIGURE 2: USING DGEBA EPOXY RESIN WITH ANCAMINE 2264 AND ANCAMINE 2167 CAN REDUCE FORMULATION VISCOSITY





FIGURE 3: ANCAMINE 2264 AND ANCAMINE 2167 CAN REDUCE RESIN LOSS DURING INITIAL STAGE OF SURE



During the initial stage of cure, the viscosity of the epoxy matrix decreases and then rapidly builds to gelation as the composite part is heated. The magnitude and duration of this initial viscosity drop can influence the loss of matrix resin and/or part integrity. Ancamine 2264 and Ancamine 2167 curing agents exhibit minimal viscosity reduction, with minimum viscosities as much as four times that of an aromatic diamine (methylenedianoline)-cured formulation. Furthermore, as shown in figure 3, the poly-cycloaliphatic polyamine curing agent formulations begin to increase viscosity rapidly after less than 10 minutes.

The low-temperature reactivity of Ancamine 2264 and Ancamine 2167 curing agents allows for reduced cure times or lower cure temperatures compared with higher activation temperature aromatic diamines. This can translate into higher throughput capability. The recommended cure schedule of 0.5 hours at 176°F followed by 1 to 2 hours at 338 °F is designed to maximize development of cure and productivity. This cure schedule may require adjustment to accommodate part thickness, part geometry or heat transfer.

## EXCELLENT MECHANICAL AND THERMAL PERFORMANCE

Formulations of Ancamine 2264 and Ancamine 2167 curing agents can exhibit the high strength and modulus characteristic of aromatic diamine-cured systems, combined with the ductility and toughness characteristic of cycloaliphatic diamine-cured systems. The strength, modulus and ductility of Ancamine 2264- and Ancamine 2167-cured systems are further enhanced when DGEBA epoxy resin is used.

TABLE 1: ANCAMINE 2264 AND ANCAMINE 2167 IMPART EXCELLENT THERMAL AND MECHANICAL PERFORMANCE

Formulations	Cure Schedule	Tensile Modulus [MPa]	Tensile Strength [MPa]	Elongation at Failure [%]	K <sub>IC</sub> , psi in	T <sub>g</sub> , [°C]
<b>Amicure® PACM/ DGEBA Epoxy Resin</b>	2 hr @ 80°C + 3 hr @ 150°C	2,310	79	7.4	710	158
<b>Ancamine 2167 DGEBA Epoxy Resin</b>	2 hr @ 80°C + 3 hr @ 150°C	2,560	76	6.9	710	163
<b>Ancamine 2264/ DGEBA Epoxy Resin</b>	2 hr @ 80°C + 3 hr @ 150°C	2,670	72	4.9	680	162
<b>MDA/ DGEBA Epoxy Resin</b>	2 hr @ 80°C + 3 hr @ 150°C	2,620	73	4.4	660	160
<b>Amicure® PACM/ DGEBA Epoxy Resin</b>	0.5 hr @ 80°C + 2 hr @ 170°C	2,400	79	6.6	-	162
<b>Ancamine 2167/ DGEBA Epoxy Resin</b>	0.5 hr @ 80°C + 2 hr @ 170°C	2,620	76	6.2	-	155
<b>Ancamine 2264/ DGEBA Epoxy Resin</b>	0.5 hr @ 80°C + 2 hr @ 170°C	2,740	74	4.8	-	156

TABLE 2: CURED DGEBF EPOXY RESIN CAN EXHIBIT IMPROVED MECHANICAL PERFORMANCE COMPARED WITH DGEBA EPOXY RESIN

Formulations	Cure Schedule	Tensile Modulus [MPa]	Tensile Strength [MPa]	Elongation at Failure [%]	T <sub>g</sub> , [°C]
Ancamine 2167/ DGEBF Epoxy Resin	2 hr @ 80°C + 3 hr @ 150°C	2,740	86	8.5	130
Ancamine 2167 DGEBA Epoxy Resin	2 hr @ 80°C + 3 hr @ 150°C	2,560	76	6.9	163
Ancamine 2264/ DGEBF Epoxy Resin	2 hr @ 80°C + 3 hr @ 150°C	3,020	92	6.9	130
Ancamine 2264/ DGEBA Epoxy Resin	2 hr @ 80°C + 3 hr @ 150°C	2,675	72	4.9	162

### SUPERIOR SOLVENT AND ACID RESISTANCE

DGEBA epoxy resin cured with Ancamine 2264 and Ancamine 2167 exhibits chemical resistance superior to common cycloaliphatic diamine-cured resins. In the case of Ancamine 2264-cured DGEBA epoxy resin, the chemical resistance approaches that exhibited by aromatic amine-cured epoxy resin. The chemical resistance of an Ancamine 2264-cured system can be further enhanced using novolac epoxy resins.

FIGURE 4: POLYCYCLOALIPHATIC POLYAMINE CURING AGENTS EXHIBIT SUPERIOR CHEMICAL RESISTANCE




TABLE 3: FORMULATIONS CURED WITH ANCAMINE 2264 AND ANCAMINE 2167 CURING AGENTS EXHIBIT SUPERIOR SOLVENT, CAUSTIC, AND WATER RESISTANCE

Formulations with DGEBA Epoxy Resin:				
% Weight Change @ 120 Days, 73°F Immersion				
Reagent	Amicure PACM	Ancamine 2167	Ancamine 2264	MDA
10% Sodium Hydroxide	1.5	1.4	1.5	1.5
10% Ammonium Hydroxide	1.8	1.7	1.8	1.9
10% Nitric Acid	3.8	3.7	3.4	2.5
30% Sulfuric Acid	1.9	1.8	1.8	1.8
25% Acetic Acid	15.0	13.0	11.5	1.8
Methanol	8.0	7.0	5.7	5.0
Acetone	6.4	6.9	6.5	6.2
Toluene	0.7	0.3	0.6	-
Ethanol	1.2	0.4	0.5	-
Deionized Water	1.2	1.6	1.7	1.9

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

**Disclaimer**

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

**EVONIK OPERATIONS GMBH**

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**EVONIK CORPORATION**

Business Line Crosslinkers  
7201 Hamilton Blvd.  
Allentown, PA 18195  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

**EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.**

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

