

ANCAMINE[®] 2264**Curing Agent****DESCRIPTION**

Ancamine 2264 is a polycycloaliphatic polyamine designed for use in the elevated temperature cure of epoxy resins. The low viscosity and relatively long pot-lives at moderate temperatures coupled with the excellent mechanical properties and high heat resistance following cure make Ancamine 2264 an ideal alternative to aromatic diamines. Applications for Ancamine 2264 include filament winding, laminating, casting and tooling.

TYPICAL PROPERTIES

Property	Value	Unit
Appearance	Free flowing light brown liquid	
Colour	8	Gardner
Viscosity @ 25°C	2100-2800	mPa.s
Specific Gravity @ 25°C	0.995	
Flash Point (closed cup)	>108	°C
Equivalent	54	Wt/{H}

SHELF LIFE

At least 24 months from date of manufacture in original sealed container stored undercover at ambient temperature away from excessive heat and humidity.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2264 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit
Mixed Viscosity at 25°C poise	63	
Gel Time (150g mix at 25°C)	140	mins

TYPICAL CURE SCHEDULE

2 h at 80°C plus 3 h at 150 °C

TYPICAL PERFORMANCE PROPERTIES (FOLLOWING 2 H AT 80°C PLUS 3 H AT 150°C)

Property	Value	Unit
Tensile Strength	71	N/mm ²
Tensile modulus	2.52	KN/mm ²
Elongation @ Break	4.6	%
Flexural Strength	115	N/mm ²
Flexural Modulus		KN/mm ²
Glass Transition Temp	164	°C

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

