Product information

ANCAMINE® 2672

Curing Agent

DESCRIPTION

Ancamine 2672 curing agent is a modified cycloaliphatic amine designed for use as a room temperature curing agent for liquid epoxy resin. Special features of this curing agent include low viscosity, allowing for higher filler loadings and the ability to cure relatively quickly at low temperatures. Ancamine 2672 curing agent is intended for use in solvent-free coatings, high film build systems, selfleveling and screed flooring applications.

TYPICAL PROPERTIES

| Property | Value | Unit | Method |
|-------------------------|---------------------|----------|---|
| Appearance | Clear, amber liquid | | |
| Colour | <8 | Gardner | ASTM D 1544-80 |
| Viscosity @ 25°C | 100-300 | mPa.s | Brookfield RVTD, Spindle 4 |
| Amine Value | 280-340 | mg KOH/g | Perchloric Acid Titration |
| Specific Gravity @ 21°C | 1.06 | | |
| Equivalent | 95 | Wt/{H} | |
| Recommended use Level | 50 | PHR | With Bisphenol A diglycidyl ether (EEW=190) |

ADVANTAGES

- Good corrosion resistance
- Excellent chemical resistance
- Good resistance to water spotting and amine blush
- Nonyl phenol and bisphenol-A free

APPLICATIONS

- Primers, sealers and coatings for concrete
- Chemical resistance tank linings
- High solid coatings
- Non colour sensitive applications



SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2672 curing agent.

TYPICAL HANDLING PROPERTIES*

| Property | Value | Unit | Method |
|----------------------------|-------|------|-----------------------------|
| Gel Time (150g mix @ 25°C) | 30 | mins | Techne GT-3 Gelation Timer |
| Thin Film Set Time @ 25°C | 5 | h | BK Drying Recorder Phase II |
| Typical cure schedule | 2-7 | days | |

TYPICAL PERFORMANCE PROPERTIES *

| Property | Value | Unit | Method |
|-----------------------------------|-------|------|---|
| Persoz Hardness (10 days at 23°C) | 300 | S | |
| Heat Distortion Temperature | 48 | °C | ASTM D648 |
| Carbamation Test | 3-4 | | ISO 2812 (Wet Patch Method), scale 1-5 (5 is best) |

*With Bisphenol A diglycidyl ether (EEW=190)



Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers Paul-Baumann-Str. 1 45764 Marl Germany

www.evonik.com/crosslinkers

Sample Request: APCSE@evonik.com Crosslinkers-Samples@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers 7001 Hamilton Boulevard Trexlertown, PA 18087 USA

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers 55, Chundong Road Xinzhuang Industry Park Shanghai, 201108 China CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

