

Product information

ANCAMINE[®] 2760

Curing Agent

DESCRIPTION

Ancamine 2760 curing agent is a modified cycloaliphatic amine adduct specifically designed as an ambient temperature curing agent for liquid epoxy resin. The product has a low viscosity and provides an excellent balance of properties in terms of handling, cure speed and UV durability.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear light yellow liquid		
Colour	max 2	Gardner	ISO 4630
Viscosity @ 25°C	300-600	mPa.s	ISO 2555
Amine Value	235-275	mg KOH/g	DIN 16945
Specific Gravity @ 21°C	1.02		ISO 2811
Equivalent	115	Wt{H}	
Recommended use Level	60	PHR	With bisphenol-A based epoxy resin (EEW=190)

ADVANTAGES

- Long working time
- Very good surface appearance
- Excellent colour and colour stability

APPLICATIONS

- Chemical resistant coatings
- Self levelling flooring
- Floor coatings
- Tile grouts

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

PACKAGING AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2760 curing agent.

PROPERTIESTYPICAL HANDLING PROPERTIES 23°C, 50% RH*

Property	Value	Unit	Method
Mix viscosity	2000-2500	mPa.s	ISO 2555
Gel Time	50-60	mins	Techne Gelation Timer, 150 g mix
Thin Film Set Time	7	h	ASTM D 5895 – Dry hard time
PersoZ Hardness after 1 / 7 days	220/320	s	ISO 1522
Shore Hardness after 1 / 7 days	80/85		ISO 868
Typical cure schedule	2-7	days	

*With bisphenol-A based epoxy resin (EEW=190)

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

