

Product information

ANCAMINE[®] 2768

Curing Agent

DESCRIPTION

Ancamine 2768 curing agent is a modified cycloaliphatic polyamine intended for use as a room temperature curing agent for liquid epoxy resin. The product offers broad balance of chemical resistance and surface appearance with a long working pot life. Ancamine 2768 curing agent provides high mechanical build, rapid cure and is particularly suitable for lower temperature use.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Light Yellow liquid		
Colour	max 4	Gardner	ASTM D 1544
Viscosity @ 25°C	50-250	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	320-370	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	1.0		
Equivalent	95	Wt{H}	
Recommended use Level	50	PHR	Cured with bisphenol-A based epoxy resin (EEW=190)

ADVANTAGES

- Low viscosity
- Good low temperature cure speed
- Long working pot-life

APPLICATIONS

- Industrial primers, screeds and grouts
- High solid coatings

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2768 curing agent.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit	Method
Gel Time @ 25°C	30-40	mins	Techne GT-3 Gelation Timer, 150 g mix
Thin Film Set Time @ 25°C	4.0	h	ASTM D 5895 - BK Drying Recorder, Phase 3
Hardness Shore D 7 d @ 25°C	85		ASTM D 2240
Hardness Shore D 24h @ 10°C	83		ASTM D 2240
Typical cure schedule	2-7	days	

TYPICAL PERFORMANCE PROPERTIES*

Property	Value	Unit	Method
Compressive Strength	90	MPa	ASTM D 695
Compressive Modulus	2	GPa	ASTM D 695
Carbamation Resistance @ 25°C	3		ISO 2812 (wet patch method), Scale 1-5, 5=best

*Cured with bisphenol-A based epoxy resin (EEW=190)

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

