

Product information

ANCAMINE[®] 2927

Curing Agent

DESCRIPTION

Ancamine[®] 2927 curing agent is designed to have a good balance of long latency and relatively low temperature cure with liquid epoxy resin. The low viscosity enhances the fabric wetting, minimizes material waste and improves overall throughput. It is recommended for use in cured-in-place-pipe and composites applications.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Amber liquid		
Colour	≤ 12	Gardner	ASTM D 1544
Viscosity @ 25°C	100-220	mPa.s	Brookfield DV2T, spindle SC4-21
Thermal Performance (Tg)	65	°C	DIN EN ISO 11357
Specific Gravity @ 25°C	1.02	g/cm ³	OE CD 109
Equivalent	28	Wt/[H]	
Recommended use Level	15	PHR	With bisphenol-A based epoxy resin*
Mix Viscosity @ 30 °C	2,400	mPa.s	DIN EN ISO 3219
Time to 10,000 mPa.s @ 30 °C	873	min	DIN EN ISO 3219

*(EEW=190)

ADVANTAGES

- Long pot life
- Excellent adhesion
- Good mechanical properties
- Low viscosity
- Solvent free

APPLICATIONS

- Cured-In-Place Pipe
- Composites – Filament winding, VARTM

TYPICAL CURE SCHEDULE

2 hrs @ 75°C or 3 hrs @ 65°C
Induction time is important to consider. See page 3

MECHANICAL PERFORMANCE – CAST PANEL *

Property	Value	Unit	Method
Formulation	A	Bisphenol A	Epoxy Resin (EEW 190) + Ancamine 2927
Flexural Strength	117	MPa	ASTM D790
Flexural Modulus	430	GPa	ASTM D790
Tensile Strength	75	MPa	ASTM D638
Tensile Modulus	3000	GPa	ASTM D638
Tensile Elongation @ Break	3.8	%	ASTM D638


*Cure schedule for cast panels 75°C – 2 hours

STORAGE LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.


PACKAGING AND HANDLING

Refer to Ancamine® 2927 Material Safety Data Sheet



*Figure 1. Reactivity profile at different temperature and time (24 and 30h). (EEW190): Ancamine® 2927

Ten pounds of formulation “A” was mixed in a bucket and held at 25°C, to understand the stability of the formulation in the presence of a larger mass. Samples were taken after 24 and 30h from the bucket to run reactivity at 65°C and 75°C. Figure 1 shows the reaction kickoff time at different induction times and temperatures.



*Figure 2. Reactivity profile at different temperature and time (3,7 and 10d). (EEW190): Ancamine® 2927

Figure 2 shows the reaction kickoff times at when bucket was stored at 5°C. Samples were taken after 3, 7 and 10 days from the bucket run reactivity at 65°C and 75°C.

The induction time is defined by the storage temperature. Lower the storage temperature longer the induction time. The users need to identify the ideal storage and cure temperature parameters to minimize the reaction kickoff time and resin dripping from the felt. The users have the flexibility to select time and temperature that suit their needs.

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

