

ANCAMINE® TEPA**Curing Agent****DESCRIPTION**

Ancamine TEPA curing agent is a standard commercial grade of tetraethylene pentamine. It is less corrosive and has a lower vapor pressure than either Ancamine DETA or TETA curing agents, and is also less hygroscopic and less prone to carbamation.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear amber liquid		
Color	2	Gardner	ASTM D1544-80
Viscosity @ 25°C	80	mPas	Brookfield, ASTM D445-83
Density @ 25°C	0.995	g/cm ³	
Flash Point (closed cup)	185	°C	
Equivalent	31	Wt{H}	
Recommended Use Level	16	phr, EEW=190	Some latitude is possible

ADVANTAGES

Extended pot life and less tendency to blush compared with other unmodified aliphatic amines.

APPLICATIONS

- Solvent-based baked coatings
- Encapsulation

SHELF LIFE

At least 18 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet on Ancamine TEPA curing agent.

TYPICAL CURE SCHEDULE

- 2–7 days at room temperature.
- Gel at room temperature plus 2 h at 100°C.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit
Gel Time (150g mix @ 25°C)	35	min

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

