

Product information

ANCAMINE[®] 1693

Curing Agent

DESCRIPTION

Ancamine[®] 1693 curing agent is a very low viscosity modified cycloaliphatic amine designed as an ambient-temperature curative for liquid epoxy resins. The product can be co-cured with Ancamide[®] 506 curing agent to extend the pot life or it can be accelerated with modified aliphatic amines.

TYPICAL PROPERTIES

Property	Value	Unit
Appearance	Light Yellow Liquid	
Colour	3	Gardner
Viscosity @ 77°F	100	cP
Amine Value	310	mg KOH/g
Specific Gravity @ 77°F	1.04	
Density @ 77°F	8.7	lb/gal
Flash Point (closed cup)	208	°F
Equivalent Wt{(H)}	96	
Recommended use Level	50	phr, EEW=190

ADVANTAGES

- Low viscosity
- Very good chemical resistance to acids, organic solvents and alcohols (see following tables)
- DOT noncorrosive

APPLICATIONS

- Solvent-free and high-solids coatings
- Self-leveling and mortar flooring
- Chemically-resistant linings

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 1693 curing agent.

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

TYPICAL CURE SCHEDULE

**7 days at ambient temperature.
Gel at ambient temperature plus 2 hours at 212°F.**

TYPICAL HANDLING PROPERTIES

Property	A*	B*	Unit
Use Level	50	49	phr
Mixed Viscosity @ 77°F	-	580	cP
Gel Time (150g mix @ 77°F)	52	97	Min
Thin Film Set Time @ 77°F	9	12	h

TYPICAL PERFORMANCE PROPERTIES

Property	A*	B*	Unit
Glass Transition Temperature	121	111	°F
Compressive Strength @ Yield	-	7,400	psi
Compressive Modulus	-	262	thousand psi
Tensile Strength	-	4,600	psi
Tensile Modulus	-	214	thousand psi
Tensile Elongation @ Break	-	20	%
Flexural Strength	7,500	7,700	psi
Flexural Modulus	-	274	thousand psi
Bond Strength (mild steel to mild steel)	2,550	-	psi

A* Ancamine 1693 curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

B* Ancamine 1693 curing agent with 90% DGEBA resin (EEW=190) and 10% Epodil® 748 diluent (C12-C14 alkyl glycidyl ether).



SUPPLEMENTAL DATA

CHEMICAL RESISTANCE

Chemical immersion studies following ASTM D543 were performed using Ancamine 1693 formulations cured for 7 days at 77°F. Ancamine 1693 curing agent was mixed in the recommended use levels with the following resins:

- 100% Bisphenol-A based liquid resin (EEW=190)
- 100% Bisphenol-F based liquid resin (EEW=172)
- 60 % Bisphenol-F (EEW=172) / 40% multifunctional epoxy novolac (EEW=176) resin blend
- 10% Cresyl glycidyl ether (CGE - Epodil® 742 reactive diluent) diluted Bisphenol-A resin (EEW=188)

Three samples were tested for each reagent. Table 1 shows the percent weight gain or loss after 3 days and 28 days for each of these formulations immersed in various chemicals at 77°F.

TABLE 1: CHEMICAL RESISTANCE FOR ANCAMINE 1693 FORMULATIONS % WEIGHT CHANGE AS A FUNCTION OF TIME

Reagent	with Bis-A Based		with Bis-F Based		with 60% Bis-F / 40%		with 10% CGE	
	Resin (EEW=190)		Resin (EEW=172)		Novolac		Diluted Bis-A	
	3 days	28 days	3 days	28 days	3 days	28 days	3 days	28 days
Deionized Water	0.53	1.59	0.55	1.62	0.62	1.71	0.47	1.39
Methanol	8.46	8.21	7.29	7.28	8.25	9.69	9.09	6.25
Ethanol	1.97	5.57	1.42	4.25	1.62	4.59	2.25	5.81
Toluene	1.37	-	0.13	1.98	0.06	1.32	2.62	22.15
Xylene	0.11	1.67	-0.03	0.10	0.02	0.05	0.04	2.87
Butyl Cellosolve	0.98	3.61	0.28	0.98	0.35	1.11	1.37	4.48
MEK	15.62	11.88	14.30	5.33	14.63	4.54	16.12.	11.45
10% Lactic Acid	0.65	2.38	0.84	2.94	1.12	3.46	0.72	2.39
10% Acetic Acid	1.68	5.62	1.92	6.58	2.50	7.51	1.69	5.25
70% Sulfuric Acid	0.06	-0.05	0.03	-4.32	0.04	0.11	-0.05	-0.17
98% Sulfuric Acid	Dest.	Dest.	1.86	-3.20	0.65	0.27	Dest.	Dest.
50% Sodium Hydroxide	0.01	-0.04	-0.04	-0.12	-0.11	-0.25	-0.21	-0.33
10% Sodium Hypochloride	0.54	1.26	0.46	1.14	0.43	0.94	0.48	1.23
1,1,1 Trichloroethane	3.02	15.91	0.01	0.20	0.05	1.07	0.01	0.40

Dest. = Samples destroyed

Spillage resistance studies were conducted on Ancamine 1693 curing agent formulated with a 90% bis-A resin (EEW=190) and 10% Epodil 748 diluent (C12-C14 alkyl glycidyl ether) blend. Samples were cured for 7 days at 77°F; three samples were tested for each reagent. The immersion/recovery schedule for the testing is shown in Table 2. Percentage weight change and Shore D hardness were measured after each of the immersion periods. The samples were then allowed to recover before reimmersion for the next time period. Hardness retention is relevant in flooring applications where it indicates the ability of the floor to support traffic after exposure to chemical spills. Results of this study are presented in Table 3.

TABLE 2: SPILLAGE RESISTANCE TEST METHOD SCHEDULE

Castings of 1/8" thickness are immersed for specified time period. Sample is then removed, weighed, and hardness tested immediately. Sample is then allowed to recover for specified time before re-immersion.

3 h imm → test → 24 h recover → 24 h imm → test → 24 h recover → 3 day imm → test → 3 day recover → 7 day imm → test → 7 day recover → 28 day imm → test → 7 day recover → 90 day imm → test

TABLE 3: SPILLAGE RESISTANCE FOR ANCAMINE 1618 WITH 90% DGEBA / 10% EPODIL 748 % WEIGHT CHANGE AND SHORE D HARDNESS AS A FUNCTION OF TIME

Reagent	Initial	After 3 hr		After 24 hr		After 3 days		After 7 days		After 28 days		After 90 days	
	Hard.	% wt.	Hard	% wt.	Hard	% wt.	Hard	% wt.	Hard	% wt.	Hard	% wt.	Hard
% Acetic Acid	79	0.36	77	1.15	72	2.34	65	3.70	67	6.19	64	9.8	64
10% Lactic Acid	79	0.13	79	0.45	79	0.95	78	1.52	77	2.39	76	3.22	70
Toluene	79	0.17	75	6.08	60	24.91	52	22.69	44	19.97	37	15.74	52
Xylene	79	0.01	76	0.61	72	4.35	60	10.02	42	18.22	45	15.14	48
Trichloroethane	79	0.20	75	3.22	70	12.64	55	22.8	50	41.71	43	39.71	39
Methanol	79	1.98	66	5.50	39	9.04	25	3.95	40	2.19	60	1.42	57
Ethanol	79	0.46	75	1.33	71	2.56	68	3.84	66	3.20	63	-1.17	68
Butyl Cellosolve	79	0.26	75	1.08	70	2.41	68	3.31	66	6.75	63	15.93	57
MEK	79	5.66	56	19.76	20	15.21	20	14.29	22	14.33	28	14.09	27
Skydrol	79	-0.01	78	-0.13	78	-0.24	78	-0.37	77	-0.67	79	-1.17	54
70% Sulfuric Acid	79	0.05	80	0.01	79	-0.02	79	-0.02	81	-0.09	81	-0.05	79
98% Sulfuric Acid	79	-21.35	74	Destroyed									
Deionized Water	79	0.11	78	0.03	79	0.58	78	0.95	79	1.27	77	1.04	77
50% Sodium Hydroxide	79	-0.02	79	-0.11	80	-0.14	80	-0.20	80	-0.35	80	-0.54	65
Bleach	79	0.10	78	0.28	78	0.54	78	0.77	78	0.74	78	-0.72	67

Dest.: Samples cured for 7 days at 77°F before testing



These studies show that Ancamine 1693 curing agent imparts good chemical resistance to all types of reagents. Compared with most curing agents, Ancamine 1693 provides excellent resistance to alcohols and to methyl ethyl ketone (MEK). Chemical resistance of 1693-based formulations can be optimized for specific chemicals using different resin blends. The chemical resistance imparted by Ancamine 1693 curing agent makes it useful in formulating chemically resistant coatings and secondary containment linings. For information on the chemical resistance of many other Evonik curing agents, please refer to publication number 125-9326 (Rev 1996): "Chemical Resistance for Ambient Cure Epoxy Formulations."

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

