

ANCAMINE[®] 2089M**Curing Agent****DESCRIPTION**

Ancamine 2089M curing agent is a modified aliphatic amine for use as an ambient temperature curing agent for liquid epoxy resins. It imparts rapid development of properties at ambient and low temperatures with very good film appearance.

TYPICAL PROPERTIES

Property	Value	Unit
Appearance	Pale, Yellow Liquid	
Colour	2	Gardner
Viscosity @ 77°F	100	cP
Specific Gravity @ 77°F	0.947	
Amine Value	395	mg KOH/g
Flash Point (closed cup)	266	°F
Equivalent	75	Wt/{H}
Recommended Use Level	40	phr, EEW=190

ADVANTAGES

- Rapid ambient and low temperature cure
- High-gloss blush-free films
- High reactivity
- Low viscosity

APPLICATIONS

- Solvent-free and high-solids coatings
- Crack injection
- Adhesives and concrete patching compounds
- Accelerator for amine-cured coatings and floorings

For additional information on chemical resistance, physical properties and use of Ancamine 2089M as an accelerating curing agent, refer to "Epoxy Curing Agents for Flooring Applications."

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2089M curing agent.

TYPICAL CURE SCHEDULE

1-2 days at ambient temperature.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit
Mixed Viscosity @ 77°F /25°C	2,540	cP
Gel Time (150g mix @ 77°F /25°C)	15	min
Thin Film Set Time:		
@ 77°F	2.0	h
@ 40°F	5.0	h
Peak Exotherm [100g mix @ 77°F (25°C)]	146	°F
Peak Exotherm Time	20	min

TYPICAL PERFORMANCE*

Property	Value	Unit
[7 day cure @ 77°F (25°C)]		
Compressive Strength	12,300	psi
Compressive Modulus	267	thousand psi
Tensile Strength	11,000	psi
Tensile Modulus	577	thousand psi
Tensile Elongation @ Break	3.3	%
Flexural Strength	18,000	psi
Flexural Modulus	648	thousand psi
Heat Deflection Temperature (ASTM D648-264 psi)	133	°F
Barcol Hardness	81	Model GYZJ-935
Bond Strength (mild steel to mild steel)	940	psi

*Ancamine 2072 curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.



SUPPLEMENTARY DATA

Ancamine 2089M as an accelerator for cycloaliphatic, aliphatic and amidoamine curing agents.

Ancamine 2089M P.B.W.	Ancamine 1618 P.B.W.	Ancamine 2021 P.B.W.	Ancamine 506 P.B.W.	Loading of Blend (phr)	150g mix Gel Time @ 77°F (min)	0.2mm films Set Time @ 77°F (h)
100	-	-	-	40	15	2
80	20	-	-	43	17	3
60	40	-	-	46	20	4
40	60	-	-	50	25	4.5
20	80	-	-	55	27	5.5
-	100	-	-	60	38	7.5
80	-	20	-	41	17	2.5
60	-	40	-	42	19	3.5
40	-	60	-	43	25	4.5
20	-	80	-	44	29	6
-	-	100	-	45	43	8.5
80	-	-	20	42	19	3
60	-	-	40	43	23	5
40	-	-	60	45	32	8
20	-	-	80	48	41	16
-	-	-	100	50	350	23

Footnotes:

- (1) EPON 828/DER 331 resin was used as standard liquid bisphenol-A epoxy.
- (2) Gel times were measured in air according to BS 2782.
- (3) Thin film set times were measured on a Beck-Koller drying tester.
- (4) Ancamine 1618 curing agent is a standard cycloaliphatic amine adduct curing agent.
- (5) Ancamine 2021 curing agent is a modified aliphatic amine adduct.
- (6) Ancamine 506 curing agent is a long pot life amidoamine.
- (7) All the above combinations with Ancamine 2089M yield high gloss films. This compares favorably with coatings derived from conventional fast-curing aliphatic amine (Ancamine 1768 curing agent) accelerated blends, which at levels in excess of 15 P.B.W. of Ancamine 1768 yield greasy films.

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

