

Product information

ANCAMINE[®] Y

Curing Agent

DESCRIPTION

Ancamine Y curing agent is an aromatic amine designed for curing liquid epoxy resins at elevated temperatures. Ancamine Y curative exhibits the longest pot life of MDA-based aromatic amines with excellent chemical resistance, high mechanical strength, and high temperature tolerance.

TYPICAL PROPERTIES

Property	Value	Unit
Appearance	Yellow to Light Brown	
Colour	6	Gardner
Viscosity @ 77°F / 25°C	1,200	cPs
Specific Gravity @ 77°F / 25°C	1.14	
Equivalent Wt/{H}	48.5	
Recommended Use Level	27.0	PHR

APPLICATIONS

- Laminates and Composites
- Filament Wound Pipe / Liners / Fittings

RECOMMENDED PROCESSING

- Filament Winding
- Resin Transfer Molding
- Fiber Impregnation in a Controlled Environment

ADVANTAGES

- Excellent physical properties
- High heat deflection temperature
- Good pot life
- Good chemical resistance

SHELF LIFE

At least 60 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine Y curing agent.

TYPICAL CURE SCHEDULE

2 hours at 176°F, then 3 hours at 302°F
2 hours at 80°C, then 3 hours at 150°C

TYPICAL HANDLING PROPERTIES *

Property	Value	Unit
Mixed Viscosity @ 140°F / 60°C	235	cPs
Gel Time (150g mix @ 77°F / 25°C)	480	min
Time to 10,000 cPs @ 140°F / 60°C	220	min

TABLE 3: THERMAL PERFORMANCE *

Property	SI	English
Glass Transition Temperature (DSC second scan)	167 °C	333 °F

TABLE 4: MECHANICAL PERFORMANCE - CAST PANEL *

Property	SI	English
Flexural Strength	177 MPa	25.7 ksi
Flexural Modulus	3.7 GPa	0.54 Msi
Tensile Strength	60 MPa	8.7 ksi
Tensile Modulus	3.3 GPa	0.48 Msi
Tensile Elongation @ Break	4.2%	4.2%
Compressive Strength	120 MPa	17.4 ksi
Compressive Modulus	2.1 GPa	0.30 Msi
Izod Impact Strength	33.6 J/m	0.6 ft-lb/in

* Ancamine Y curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=180) epoxy resin

TABLE 5: MECHANICAL PERFORMANCE - COMPOSITE PANEL *

Property	SI	English
ILSS 0° Longitude	70 MPa	10.1 ksi
Flexural Strength - Composite 0° Longitude	1269 MPa	184.0 ksi
Flexural Modulus - Composite 0° Longitude	55.2 GPa	8.0 Msi


* Ancamine Y curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=180) epoxy resin

MDA-BASED AROMATIC AMINES SUPPLEMENTARY DATA

REACTIVITY AND DEVELOPMENT OF CURE

Ancamine® DL50, Ancamine 1482, Ancamine Y, and Ancamine Z curing agents offer a range of reactivity with epoxy resin while maintaining the high mechanical properties and chemical resistance typical of aromatic amines. Blended with standard diglycidyl ether of bisphenol-A (DGEBA) epoxy resin, systems can provide a 2 to 3.5 hour pot life even at 60°C. Figure 1 shows the viscosity build of aromatic amines with EEW=180DGEBA resin at 60°C.

FIGURE 1: AROMATIC AMINE DGEBA (EEW=180) MIX VISCOSITY BUILD AT 60°C



CHEMICAL RESISTANCE

DGEBA epoxy resin cured with Ancamine DL-50, Ancamine 1482, Ancamine Y, and Ancamine Z curatives exhibits excellent chemical resistance. with DGEBA resin. Chemical resistance can be further enhanced using novalac epoxy resins.

TABLE 6: CHEMICAL RESISTANCE TEST

Formulation: DGEBA Epoxy Resin Mix (EEW=180)

Cure Schedule: 2 h @ 80°C, then 3 h @ 150°C

Specimen: 1" X 3" X 1/8" Disc

Test: % Weight gain after 120 days immersion @ 73°F / 24°C

Reagent	Ancamine DL 50	Ancamine 1482	Ancamine Y	Ancamine Z
Water (Distilled)	0.6%	0.9%		
Jet Fuel C	0.1%		0.6%	0.3%
Toluene	0.2%	0.4%	0.2%	0.1%
Acetone	10.7%		15.9%	20.1%
Ethanol	0.8%	0.5%	0.6%	0.7%
Methanol	5.0%	1.4%		
HNO ₃ (20%)	0.9%	1.0%	0.3%	0.3%
Acetic Acid (25%)	1.4%	0.7%	1.1%	1.1%

PERFORMANCE PROPERTIES

Ancamine[®] DL50, Ancamine 1482, Ancamine Y, and Ancamine Z curing agents are mixtures of aromatic amines designed for the curing of liquid epoxy resins at elevated temperatures. See table 7 for a comparison of typical properties.

TABLE 7: PERFORMANCE PROPERTIES

Typical Properties	Ancamine DL 50		Ancamine 1482		Ancamine Y		Ancamine Z	
	SI	English	SI	English	SI	English	SI	English
Appearance	Yellow to Light Brown		Dark Brown		Liquid Yellow to Light Brown		Dark Liquid	
Color (Gardner)	9		18		6		No Data	
Viscosity @ 77°F / 25°C	55,000 @ 30°C		1,900 cP		1,200 cP		2,200 cP	
Specific Gravity @ 77°F / 25°C	1.10		1.15		1.14		1.14	
Equivalent Wt/{H}	51		42		48.5		38	
Use Level (PHR)	28.0		23.0		27.0		21.0	
Typical Handling Properties⁽¹⁾								
Mixed Viscosity @ 140°F / 60°C	335 cP		235 cP		235 cP		185 cP	
Gel Time (150g mix @ 77°F / 25°C)	480 min		960 min		480 min		480 min	
Time to 10,000 cPS @ 140°F / 60°C	189 min		195 min		220 min		155 min	
Thermal Performance⁽¹⁾								
Glass Transition Temperature (DSC second scan)	161°C	322°F	160°C	320°F	167°C	333°F	155°C	311°F
Mechanical Performance - Cast Panel⁽¹⁾								
Flexural Strength	175 MPa	25.4 ksi	123 MPa	17.8 ksi	177 MPa	25.7 ksi	164 MPa	23.8 ksi
Flexural Modulus	3.4 GPa	0.49 Msi	2.5 GPa	0.36 Msi	3.7 GPa	0.54 Msi	3.7 GPa	0.54 Msi
Tensile Strength	73 MPa	10.6 ksi	81 MPa	11.7 ksi	60 MPa	8.7 ksi	74 MPa	10.7 ksi
Tensile Modulus	3.2 GPa	0.46 Msi	2.8 GPa	0.41 Msi	3.3 GPa	0.48 Msi	3.7 GPa	0.54 Msi
Tensile Elongation @ Break	4.4%		5.3%		4.2%		4.4%	
Compressive Strength	121 MPa	17.5 ksi	122 MPa	17.7 ksi	120 MPa	17.4 ksi	129 MPa	18.7 ksi
Compressive Modulus	2.0 GPa	0.29 Msi	2.2 GPa	0.32 Msi	2.1 GPa	0.30 Msi	3.1 GPa	0.45 Msi
Izod Impact Strength			45.6 J/m	0.3 ft-lb/in	33.6 J/m	0.2 ft-lb/in		
Mechanical Performance - Composite Panel⁽²⁾								
ILSS 0° Longitude	74 MPa	10.7 ksi	71 MPa	10.4 ksi	70 MPa	10.1 ksi	72 MPa	10.5 ksi
Flexural Strength - Composite 0° Longitude	1172 MPa	170.0 ksi	1310 MPa	190.0 ksi	1269 MPa	184.0 ksi	1282 MPa	186.0 ksi
Flexural Modulus - Composite 0° Longitude	52.8 GPa	7.66 Msi	54.1 GPa	7.85 Msi	55.2 GPa	8.0 Msi	49.0 GPa	7.81 Msi

⁽¹⁾ Curing agents formulated with standard Bisphenol-A based (DGEBA, EEW=180) epoxy resin

⁽²⁾ VARTM Process using E-glass (275g/m²) unidirectional fiber; 60% Volume ±3%; Cured for 2 hours at 80°C ad 3 hours at 150°C



Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

