

ANQUAMINE[®] 401**Curing Agent****DESCRIPTION**

Anquamine 401 waterborne curing agent is a modified aliphatic amine supplied at 70% solids in water. It is intended for use with waterborne epoxy dispersions in two-component, ambient cure, waterborne epoxy coatings. It is also capable of emulsifying and curing liquid epoxy resins without the need for additional surfactants. Anquamine 401 delivers excellent properties in anticorrosive primers, white gloss top-coats and clear coats. Anquamine 401 can be utilised with different types of epoxy resin depending upon the properties desired.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Amber liquid		
Colour	< 12	Gardner	ASTM D 1544-80
Viscosity @ 25°C	25-40	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	240-260	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 25°C	1.09	g/ml	
Total Solids Content	69-71	wt %	
Equivalent	166	Wt/{H}	
Recommended use Level	60-90	PHR	With Bisphenol A diglycidyl ether (EEW=190)
Recommended use Level	45-55	PHR	Semi-Solid Resin Emulsion (EEW=220-250, on solids)
Recommended use Level	13-16	PHR	Solid Resin Dispersion (EEW=500-540, on solids)

ADVANTAGES

- Excellent gloss and gloss retention
- Good colour
- Visible end of pot-life
- Rapid dry time
- Excellent stain resistance
- Excellent hardness development
- Excellent abrasion resistance
- No induction time
- Good corrosion resistance

APPLICATIONS

- Floor and wall coating sealers primers and topcoats
- ECC polymer-modified mortars
- Industrial maintenance and marine primers and topcoats
- General metal primers
- Transportation primers

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Anquamine 401 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit	Method
Pot Life @ 20°C	1-1.5	h	With Bisphenol A diglycidyl ether (EEW=190)
Set to Touch @ 20°C	2.0	h	With Epiores ER8 (EEW=195)
Hard Dry @ 20°C	4.0	h	With Epiores ER8 (EEW=195)
PersoZ Hardness	270	1 day @ 20°C	With Epiores ER8 (EEW=195)
PersoZ Hardness	350	7 days @ 20°C	With Epiores ER8 (EEW=195)

TYPICAL PERFORMANCE PROPERTIES

Typical cure schedule: 2-7 days

Anquamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7201 Hamilton Blvd.
Allentown, PA 18195
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

