

Product information

ANQUAMINE[®] 731

Curing Agent

DESCRIPTION

Anquamine 731 is a water-based curing agent is specifically designed for a standard liquid epoxy resin. It is specifically designed for costeffective high-film build concrete coatings. It is particularly suitable for water-based self-leveling systems. Anquamine 731 curing agent easily emulsifies Standard liquid epoxy resins without the need for emulsifiable or pre-emulsified epoxy resins.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Amber Liquid		
Color	4	Gardner	ASTM D 1544-80
Viscosity @ 77°F	50,000	cPs	Brookfield RV, Spindle 4
Amine Value	175	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 77°F	1.06		
Total Solids Content	55	wt%	
Equivalent Wt/{H}	200		
Recommended Use Level	100	phr	EEW 190

BENEFITS

- Cost effective
- Rapid hardness development
- Excellent adhesion to concrete
- Low color and good yellowing resistance
- Excellent surface appearance even at low temperature cure
- Zero VOC

APPLICATIONS

- Self-leveling floors
- Mortars
- Grouts

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet on Anquamine 731 curing Agent.

TYPICAL CURE SCHEDULE

2 to 7 days at ambient temperature.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit	Method
Pot Life	30-45	min	

TYPICAL PERFORMANCE*

Property	Value	Unit	Method
1 day Shore D (25°C, 55% RH)	70		
7 day Shore D (25°C, 55% RH)	75		
1 day Shore D (10°C, 50% RH)	60		
7 day Shore D (10°C, 50% RH)	75		
Compressive Strength	5,800	psi	ASTM C 579 (1" cube)
Tensile Strength	1,200	psi	

* Self-leveling starting point formulation.

CURING AGENT CHARACTERISTICS

Anquamine 731 water-based curing agent is specifically designed for use in water-based high film build applications, such as self-leveling, mortar or grout applications. High-film build applications often suffer from shrinkage and ultimately cracking of the coating system caused by the evaporation of water in the system. Anquamine 731 curing agent allows the formulation of self leveling systems without cracking.

The use of self leveling flooring is commonly used in concrete protection offering optimum handling properties and maximum protection of the concrete in terms of wear and tear, abrasion and chemical resistance. In self leveling systems with Anquamine 731 curing agent, the formulation binder content can be reduced compared to solvent free systems to yield a high performance waterbased self leveling system, thus providing a cost effective, optimum handling and high performance concrete protection system.

Self leveling formulations based on Anquamine 731 curing agent provide a desirable satin-finish to yield good cleanability at reduced scratch sensitivity. In addition, this system provides high resistance to impact, e.g. from falling heavy objects. Upon impact a 'dent' but no cracking will occur so that concrete will be protected without extensive repair work.

Anquamine 731 curing agent is solvent and plasticizer free allowing for the increasingly stringent emission standards to be met.

FORMULATION GUIDELINES

RECOMMEND EPOXY RESINS: Anquamine 731 curing agent exhibits good compatibility with liquid epoxy resins based on Bisphenol A or F and is equally suitable in either unmodified or modified form. Reactive diluent modified epoxy resin will offer improved handling and formulating latitude within the self-leveling system. It is recommended to use a monofunctional diluent such as Epodil® 748 diluent at up to 15%. Alternatively, difunctional reactive diluents such as Epodil 757 can be used.

DEFOAMER/WETTING AGENTS: Defoamers such as Surfynol® DF66 and BYK® 045 defoamers are very suitable for use in the self-leveling formulation to give optimum air release and surface properties. ZetaSpers® 1600 and Disperbyk® 190 can be used to effectively aid in wetting pigments and increasing flow and leveling properties to give a system which yields good surface and flow properties.

FILLERS: The filler package is optimized with the correct balance of sand grades to yield a system with good flow and leveling. Quartz sand and barytes (BaSO₄) are recommended to be used in combination with dry pigments or pre-dispersed pigment pastes to give the desired performance and aesthetics.

STARTING POINT FORMULATION — WATERBORNE SELF LEVELING FLOOR

This formulation is ideally suited as a self leveling compound for concrete floors.

Nb.	A-Component		Supplier	By Weight
1.	Liquid Epoxy Resin	EEW=190	Various	8.1
2.	Reactive Diluent	Epodil® 748 diluent	Evonik	1.1
				9.2
B-Component				
3.	Curing agent	Anquamine® 731 curative	Evonik	9.5
4.	Defoamer	Byk® 045	BYK	0.80
5.	Diluent	DI Water	Local	10.30
6.	Pigment TiO ₂	Kronos® 2160 pigment	Kronos	4.00
7.	Filler BaSO ₄	Cimbar™ 325 filler	Cimbar	13.00
8.	Rheology Modifier	Rhodopol 23 xanthan gum (3% water)	Rhodia	0.4
				38.00
B-Component Manufacture Procedure:				
<ul style="list-style-type: none"> • Charge components 3-4 and stir homogeneous at low shear • Slowly charge components 5-8 while increasing speed shear • Mix at medium shear for 15 minutes 				
C-Component				
9.	Quartz Sand	US Silica Sil-co-sil® 106	US Silica	28.00
10.	Quartz Powder	US Silica NJ #70	US Silica	34.00
				62.00
	Total			109.2

DESCRIPTION: This self leveling flooring system is prepared by mixing Component A with Component B for 2-3 minutes using low shear mechanical mixing to produce a homogeneous mixture. Component B may have some soft settlement that should be thoroughly mixed prior to adding Component A. Add component C and mix for 2-3 minutes using low shear mechanical mixing to produce a homogeneous mixture. Once mixed it can be applied to the concrete substrate using a squeegee or similar tool to spread the mixture and followed by spike rolling in order to promote de-aeration.

TECHNICAL DATA

Property	Value	Unit	Method
Mixing ratio A:B:C	9.2 : 38 : 62	Weight	
Adhesion to Concrete	400	Psi	100% failure in concrete
Shore D Hardness			
1 Day	70		@ 25 °C
7 Days	75		@ 25 °C
1 Day	60		@ 25 °C
7 Days	75		@ 25 °C
Chemical Resistance 24 h, spot test			
3% Acetic Acid	No Effect		
10% NaOH	No Effect		
Ethanol	No Effect		
Xylene	No Effect		
Water	No Effect		
Flow	8	Inches	225 gram mixed mass in 3" ID pipe, flow on a Teflon sheet
Gloss	10-15	60°	
Working Time	30-45	Minutes	
Binder Content (mix)	13.3	Wt. %	
Solids Content (mix)	86	Wt. %	
Stain Resistance 24 h, spot test			
Red Wine	No Effect		
Tea	No Effect		
Coffee	No Effect		
Cola	No Effect		
Mustard	Slight stain		
Ketchup	Slight stain		

Anquamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

