

Product information

DICYANEX[®] 1200

Curing Agent

DESCRIPTION

Dicyanex 1200 curing agent is a micronized grade of dicyandiamide containing 2.5% of an inert flow control additive to inhibit clumping and improve handling. It is designed for use as a latent curing agent for epoxy resins.

TYPICAL PROPERTIES

Property	Value	Unit
Appearance	White, Crystalline Particles	
Melting Point	405-412	°F
Particle Size:		
90 %	<35	microns
50 %	<13	microns
Nitrogen as % of Dicyandiamide	99	
Equivalent Wt/{H}	21	
Recommended Use Level (EEW=190)	4-15	phr

ADVANTAGES

- Fine particle size provides enhanced reactivity versus coarser grades
- Maximum dispersibility in liquid resin due to high level offlow additive
- Shelf stability of up to 6 months @ 77°F (25°C) in properly formulated Systems
- Activation temperature can be varied easily from 356°F - 203°F (180°C - 95°C) with appropriate accelerator selection

APPLICATIONS

- One-component adhesives
- Recreational and industrial pre-preg Composites
- Powder coatings

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Dicyanex 1200 curing agent.

TYPICAL CURE SCHEDULE

- 1-2 h @ 356°F (180°C)
- 45 min @ 250°F (120°C) with 0.5 parts

TYPICAL HANDLING PROPERTIES

Gel Time (month) [150 g mass @ 77°F (25°C)] 12

SUGGESTED ACCELERATORS

Ancamine® 2014AS/2014FG
Amicure™ UR/UR2T
Imidazoles

TYPICAL PERFORMANCE

Property	Value	Unit
T _g *	250	°F
when accelerated with Ancamine 2014AS	115	

* Measured using DSC with 50°F (10°C)/min ramp. Value will be higher when accelerated with an imidazole.

Dicyanex® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

**EVONIK SPECIALTY CHEMICALS
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

