

EPODIL[®] 748**Reactive Diluent****DESCRIPTION**

Epodil 748 reactive diluent is an aliphatic glycidylether, comparable to Epoxide 8.1 It is a monofunctional reactive diluent used to reduce the viscosity of epoxy resin systems. Since monofunctional diluents, in general, cause molecular weight chain termination, the minimum amount necessary to achieve the desired viscosity reduction should be used.

Epodil 748 reactive diluent is particularly useful where low volatility levels are required so that problems in poorly ventilated areas are minimized. It can be used in compliance with 21 CFR 175.300, 21 CFR 175.105, 21 CFR 176.180 and 21 CFR 177.1650 as a component of FDA-compliant formulations. Slight increases in pot life can be expected when 5.20% of Epodil 748 reactive diluent is blended with typical liquid epoxy resins.

TYPICAL PROPERTIES

Property	Value	Unit
Appearance	Clear Liquid	
Color	100	APHA
Viscosity @ 77°F	12	cPs
Specific Gravity @ 77°F	0.890	
Flash Point (Setaflash)	>200	°F
Hydrolyzable Chloride	max 0.1	
Residual Epichlorohydrin	max 10	ppm
Weight per Gall	7.3-7.5	lb/gal
Moisture Content	max 0.1	%
Equivalent Wt{H}	290	
Recommended Use Level (EEW=190)	See Table	phr

ADVANTAGES

- Low vapor pressure and low toxicity
- Improves flexibility
- Improves adhesion to non-polar surfaces

APPLICATIONS

- Flooring, mortars and grouts
- High and 100% solids coatings
- Laminates
- Exposed aggregate

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Epodil 748 reactive diluent.

SHELF LIFE

At least 36 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

Material may crystallize or solidify upon exposure to low temperatures. Crystallized or solidified material can be utilized after melting at elevated temperatures without impacting handling or physical properties. It is recommended that the material be heated to 50-70°C while mixing continuously for 1 hour.

SUPPLEMENTARY DATA

Weight Percent Epodil 748 (%)	Viscosity @ 77°F (cPs)
Epodil 748 reactive diluent can be used as follows to lower the viscosity of a standard Bisphenol-A liquid epoxy resin (EEW=190) with an initial viscosity of 12,500 cPs:	
5	4,000
10	1,050
15	500
20	300

(1) Trademark of Proctor & Gamble Corporation

EXAMPLE IMPACT OF DILUENT ON A SIMPLE FORMULATED SYSTEM

Evonik recommends that the formulator test reactive diluents in their system for performance. The following data is provided as an example of the impact of the reactive diluent on a simple formulated system.

Property	Without Epodil 748	With Epodil 748
PersoZ hardness ² at 23°C (1 day/7day)	195/310	61/274
Phase 3 dry time ³ (h)	7:10	10:05
Tg ⁴ (1st scan)	51	48
Gel time ⁵ (min)	55	75

System :

- BADGE with 12.5 wt% Epodil 748
- Cured with Ancamine[®] 1618 curing agent at 1:1 stoichiometry

(2) BYK PersoZ pendulum tester according to ISO 1522 with 10 mil WFT at 23°C/50% RH

(3) 6 mil WFT BK Drying time recorder according to ASTM D5895 with 6 mil WFT at 23°C/50% RH

(4) TA Instruments DSC model Q200 first scan data

(5) 150g mix using TECHNE Gel-timer

Epodil[®] is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

