

**IMICURE<sup>®</sup> AMI-2T****Curing Agent****DESCRIPTION**

Imicure AMI-2T curing agent is an elevated temperature curing agent for epoxy systems. It is readily compatible with both liquid and solid epoxy resins, and because it is a catalytic curing agent, it is used at low loadings of 1-5 phr. It is a good accelerator for dicyandiamide, anhydride and phenolic curing agents.

**TYPICAL PROPERTIES**

Property	Value	Unit
Appearance	White Powder	
Purity	min 98.5	%
Imidazole	1.0	%
Water	< 0.5	%
Boiling Range	≈ 264	°C
Melting Point	136-140	°C
Solubility	Soluble in water and common polar organic solvents	
Density	0.4 - 0.6	g/ml
Flash Point (open cup)	155	°C
Recommended Use Level (EEW=190)	2-4	phr

**BENEFITS**

- Soluble in water and common polar organic solvents
- Excellent dicyandiamide accelerator
- Develops Tg ≈ 300°F (150°C) in heat-cured systems

**APPLICATIONS**

- Electrical laminates
- Adhesives
- Pre-preg composites
- Encapsulation

## SHELF LIFE

At least 12 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## STORAGE AND HANDLING

Refer to the Safety Data Sheet for Imicure AMI-2T curing agent.

## TYPICAL HANDLING PROPERTIES \*

Property	Value	Unit
4 phr, ground to 80 mesh		
Pot Life @ 25°C (200 g mass w/ 1% fumed silica)	8	h
Gel Time @ 158°F (70°C) (200g mass)	35	min

\* Imicure AMI-2T curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

Imicure® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

### Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

### EVONIK OPERATIONS GMBH

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

### EVONIK CORPORATION

Business Line Crosslinkers  
7201 Hamilton Blvd.  
Allentown, PA 18195  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

### EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

