

## Product information

# SUNMIDE<sup>®</sup> 307D-60

## Curing Agent

### DESCRIPTION

Sunmide 307D-60 is a polyamide amine in xylene and n-butanol. It displays very good thixotropic properties. Sunmide 307D-60 is most commonly used for fast cure and fast dry applications for industrial epoxy coatings.

### TYPICAL PROPERTIES

Property	Value	Unit	Method
Amine Value	120 - 140	mg KOH/g	
Color	12 max	Gardner	
Viscosity @ 25°C / 77 °F	2000-4000	mPa.s	
Non Volatile	58-62	%	
Specific Gravity	0.93		
Solvent	Xylene / n-butanol (8/2)		
Equivalent Wt/{H}	226		solid solution
	377		

### ADVANTAGES

- Fast cure
- Low toxicity
- Long pot life

### APPLICATIONS

- General epoxy coatings
- Zinc rich paints
- Adhesive for abrasive paper

### SHELF LIFE

- Stable under temperate or tropical conditions.
- Recommended shelf life – 1 year

## STORAGE AND HANDLING

Refer to the Safety Data sheet for Sunmide 307D-60 curing agent.

Sunmide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

### Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

#### EVONIK OPERATIONS GMBH

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

#### EVONIK CORPORATION

Business Line Crosslinkers  
7001 Hamilton Boulevard  
Trexlerstown, PA 18087  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

#### EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)